



revoseal

revoseal JG/JP – expert report of MPA Stuttgart

The MPA Stuttgart created a sealing performance report of 10x JG-2 gasket which were mounted on the same flange (successively).

Following leakage rate has been measured:

1 st Mounting	4×10^{-10} mbar l/s
10 th Mounting	15×10^{-10} mbar l/s

- Strict interpretation of test parameters → 40bar instead of 1bar (acc. to VDI2440)